

# iQ Toro SC

## Datasheet

Classification	Norm	Tarkett Value
Product type	ISO 10581	Permanently static conductive pressed homogeneous vinyl flooring
Binder content	ISO 10581	Type I
Commercial classification	ISO 10874	34 Very Heavy
Industrial classification	ISO 10874	43 Heavy
Technical Characteristics	Norm	Tarkett Value
Surface treatment		New iQ PUR
Surface Restoration		Yes
Total thickness	ISO 24346	2 mm
Wear layer thickness	ISO 24340	2 mm
Total weight	ISO 23997	2800 g/m <sup>2</sup>
Performance for CE Marking	Norm	Tarkett Value
Declaration of Performance #	EN 14041	0019-0038-DoP-2013-07
Reaction to fire	EN 13501-1	Bfl-s1
Reaction to fire	EN ISO 9239-1	≥ 8 kW/m <sup>2</sup>
Reaction to fire	EN ISO 11925-2	Pass
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Thermal resistance	EN 12667	~0,010 m <sup>2</sup> •K/W
Slip resistance	EN 13893	Class DS (μ ≥ 0,30)
Technical Performance	Norm	Tarkett Value
Residual indentation	EN ISO 24343-1	Required value: ≤ 0,10 mm Best measured value: 0,02 mm
Slip resistance	DIN 51130	R9
Slip Resistance	BS 7976-2	Low risk of slip
Electrical Insulation	VDE0100, Part 600	Ri ≤ 5x10 <sup>4</sup> Ohms
Electrical resistance	ESD-approval SP method 2472	R ≤ 10 <sup>9</sup> Ohms
Electrical resistance	EN 1081	R1 5x10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> Ohms / R2 5x10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> Ohms
Electrical Resistance	EN/IEC 61340-4-1, 100 V	R 5x10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> Ohms
Electrical Resistance	EN/IEC 61340-4-5	≤ 3,5x10 <sup>7</sup> Ohms
Curl resultant to heat for rolls	EN ISO 23999	≤ 8 mm
Curl resultant to heat for tiles	EN ISO 23999	≤ 2 mm
Clean room	ISO 14644-1	ISO class 4
Castor chair	ISO 4918	Suitable
Furniture leg	ISO 16581	No damage
Colour fastness to light	ISO 105-B02	≥ 7
Dimensional stability	EN ISO 23999	Average Measured Value : ≤ 0.40 %
Dimensional Stability for Tiles	EN ISO 23999	Average measured value : ≤ 0.25 %
Ease of Decontamination	ISO 8690 - DIN 25415	Excellent
Chemical resistance	ISO 26987	Excellent Resistance
Bacteria Resistance	ISO 846 Part C	Does not promote growth
Underfloor heating		Suitable (maximum 27°C)
Seam Strength Average Value	EN 684	≥ 240 N/50mm
Seam Strength Individual Value	EN 684	≥ 180 N/50mm
Sustainability performances	Norm	Tarkett Value
Recyclability through ReStart®		Recyclable
Recycled content		25,5 %
Total VOC Emissions	EN 16516	Platinum (≤ 10 µg/m <sup>3</sup> )
Dimensions and designs		
Roll		Roll 2 x 23 m
Tile		Tile 610 x 610 mm - 14 tiles=5,2 m <sup>2</sup> /box - 40 boxes/pallet
Number of designs available		14



The above information is subject to modification for the benefit of further improvement (09/08/2022). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.